

Saber S.r.l.

Via Caduti sul Lavoro, 4 - 46019 Viadana (MN) Italy
Tel: +39 0375 782083 - Fax: +39 0375 780055
info@sabercolor.com - bernini@pec.sabercolor.com
Partita IVA e Codice fiscale 00289400202
Capitale Sociale € 30.000 - REA: MN 127583

SCHEDA TECNICA MATERIA

Cod. 349. – Rev. 09/2022

| | |
|---------------------------------|---|
| CLASSIFICATION | Mineral based coating for materic/textured finish. |
| KIND OF USE | The product is indicated as a finishing layer for the protection and decoration of inner surfaces to obtain finishes of good materic/textured effect. In order to increase its brilliance, contrast and intensity of shade, the product can be waxed with our metallic Cere di Pompeii Waxes, or with our Cera Royal wax. |
| CHEMICAL COMPOSITION | Long seasoned slaked lime, marble powder, selected grits. |
| TECHNICAL DATA | Appearance: paste Specific weight: 1.500+-0.050 kg/L Color: White Viscosity of supply: 50000 +- 5000 cps Brilliance: Shiny - matt |
| APPLICATION SYSTEM | Inox (stainless steel) trowel. |
| DILUTION | Ready to use. If needed add maximum 3% of water. |
| MEDIUM OUTPUT | 1.3 – 1.7 kg/mq with two coats. |
| COV READY TO USE MIXTURE | CLASSIFICATION ACCORDING TO DIRECTIVE 2004/42/EC – Legislative decree 161/06: Cat. A/I-BA DECORATIVE EFFECTS PAINT EU limits 2010 200 gr/lt. COV OF PRODUCT 20 gr/lt |
| DRYING | <div><div><div><u>AIR DRYING at 20 ° C - 60% humidity</u></div><div>Out of touch</div><div>2 hrs</div></div><div><div>in the depth</div><div>48-72 hrs</div></div><div><div>time to paint over</div><div>8-10 hrs</div></div></div> |
| MIN. TEMPERATURE OF APPLICATION | + 5° C |
| PREPARATION OF THE SURFACE | <p>For perfectly stabilized 2 layered plaster surfaces, apply a brush coat of acrylic fixative SPECIAL FIXATIVE and then a roller coat of levelling filler DAS.</p> <p>For perfectly stabilized plaster or plasterboard supports, apply a coat of acrylic fixative SPECIAL FIXATIVE and then a roller coat of levelling filler DAS.</p> |
| APPLICATION | On well-dried base, apply the first coat of MATERIA with INOX trowel by covering the surface evenly. When the first coat is dry, apply the second coat and then the third wet on-wet. When it starts to dry, pass the clean trowel over the surface, until you get shiny and matte areas. 48-72 hours after application, wax the surface with our water-based wax CERA ROYAL or with our CERE DI POMPEI with a pearlescent effect. Both waxes can be applied with a stainless steel or plastic spatula or with a synthetic sponge. Once the wax is dry, polish with a pad or a woollen cloth. |
| CLEANING EQUIPMENT AND TOOLS | With water immediately after use. |
| NOTE | Available in buckets of 5- 24 Kg. |
| STORAGE | The product must be stored in its original intact packaging in an environment that must be protected from frost and excessive heat and therefore with a temperature not lower than +5°C and not higher than +35°C.The information relating to labelling and handling are contained in the relative safety data sheet. Liquid or solid residues and empty containers must be disposed of according to local regulations. PROTECT FROM FROST. |

The information, data and suggestions contained in this technical data sheet are exact and accurate and must therefore be considered reliable and for informational purposes only and in any case, they cannot imply a guarantee on our part, as the conditions of use are outside our strict control, therefore they do not exempt the customer from the burden and responsibility of verifying the suitability of the product for the specific use it intends.