



NAME: SESTO SENSO

SERIAL CODE: 347

CLASSIFICATION: Mineral stucco of lime paste for materic finish.

KIND OF USE : for the decoration of inner surfaces in order to obtain the traditional marbled finishing with natural shading it can also be finished to increase its brilliance with Cere di Pompei, wax Cera Royal or Alicante.

COLOUR : white

CHEMICAL COMPOSITION : lime paste, marble powders.

SPECIFIC WEIGHT: 1.600+/-0.050 kg/lt

VISCOSITY OF PRODUCT : thick paste

APPLICATION SYSTEM : inox trowel

DILUTION : 1-2% with water maximum (in summer time)

MEDIUM OUTPUT for coat mq/lt: 800-1000 gr/mq for 2 coats

DRYING : out of touch	in the depth	time to paint over
2 hrs	48-72 hrs	8-10 hrs

DRY WEIGHT RESIDUAL 62%

DRY VOLUME RESIDUAL %

TABLE DIR.2004/42/CE:

A/1-BA Product= Decorative Paint.

Limits UE(2010)= 200 gr/Lt

C.O.V. gr/Lt = 20 gr/Lt.

Dilution for application= 0% with water

C.O.V. (ready to be used) gr/Lt.= Max 20 gr/Lt.

BRILLIANCE : matt

PREPARATION OF THE SURFACE: On surface made of two-layer plaster, well prepared and levelled off, apply a coat of Acrylic primer SPECIAL FIXATIVE and then a coat of white levelling DAS. For surfaces in gypsum and plasterboard, go on with a coat of Acrylic primer SPECIAL FIXATIVE and then apply a coat of White levelling DAS.

APPLICATION CYCLES : When the surface is dry apply Sesto Senso with high thickness work the surface with buffer or special "zerbino" or spalter creating the desired design. When the surface is matt, pass more and more items with inox trowel slightly squeezing the product to create graffiti and bas-reliefs. After 48-72 hours apply on the surface with Cere di Pompei or Alicante with synthetic sponge to give the product in the engraved parts of the surface.

NOTE: available in buckets Saber of 5 KG, 24 kg and coloured after evaluating feasibility of the colour. Clean the tools with water.

Keep it in a temperature from +5°C/35°C. Protect from freezing weather

All the informations in this card are exact and accurate, as we know, so they must be considered reliable. In any case they can't mean a guarantee from our, as the conditions of its use out of our control.

