



NAME: STUCCO MANTOVANO METALLIZZATO

CODE: 1640050

CLASSIFICATION: Lime-based stucco with pearly effect based on seasoned slaked lime.

KIND OF USE: The product is indicated as a finishing layer for the protection and decoration of historic or modern interiors of remarkable architectural level. Stucco Mantovano Metallizzato has a spatula-effect finish with pearly reflections of high visual impact.

COLOUR: Pearl.

Finish: Matte.

CHEMICAL COMPOSITION: Slaked seasoned lime, marble dust, versatic copolymer, micas.

SPECIFIC WEIGHT: 1.300+/-0.050 Kg/lt

APPLICATION: with plastic spatula - trowel.

DILUTION: Ready to use.

MEDIUM OUTPUT: 6-8 mq with two coats

DRYING: with air at 20°C and 60% relative humidity.

Application at +5° C minimum

out of touch
60minutes

in the depth
8hrs

time to paint over
4-6 hrs

TABLE DIR.2004/42/CE :

A/1-BA Product= Decorative paint

Limits UE(2010)=200 gr/Lt

C.O.V. gr/Lt=10gr/Lt.

Dilution for application= Ready to use.

C.O.V. (ready to be used) gr/Lt.= Max 10gr/Lt.

PREPARATION OF THE SURFACE: On NEW SURFACE of two-layer plaster, well prepared and levelled off, apply a coat of Acrylic primer SPECIAL FIXATIVE. For new surfaces in gypsum and plasterboard, brush thoroughly, go on with a coat of Acrylic primer SPECIAL FIXATIVE and then apply a coat of White levelling DAS.

OLD SURFACE: brush thoroughly the surface removing dust, dirt and flaking parts and apply some stucco to level off if necessary. Then proceed as new surface.

APPLICATION CYCLE: On any surface after a right base preparation, apply a coat of STUCCO MANTOVANO METALLIZZATO with plastic trowel, covering the surface evenly. On well dried surface, apply the second coat in small and messy spatula motions according to the esthetic desired effect.

To obtain more brilliance, go on with clean trowel on touch dry product.

NOTE: Available in lithographed buckets of 14 L, 4 L, 1L.

Keep it in temperature of +5°/+35°C. Protect from frost.

The information contained in this prospectus is, so far as to our knowledge is correct and accurate and must therefore be considered reliable. In any case, we cannot assume any responsibility, as the conditions of use are outside our strict control.



s.r.l. Via Caduti sul lavoro, 4 46019 Viadana (MN) ITALY - Tel. + 39 0375782083 Fax + 39 0375780055 www.sabercolor.com e-mail : info@sabercolor.com