



NAME: STUCCO VENEZIANO FONDO
CODE: 196.1000

CLASSIFICATION: Acrylic filler for base coat on interior wall surfaces.

KIND OF USE: The product is used as a base coat for the decoration of interior surfaces with Stucco Veneziano.

COLOUR: White.
Finish: Matte.

CHEMICAL COMPOSITION: Marble flour and acrylic copolymer.

SPECIFIC WEIGHT: 1,650 ± 0,070 kg/L

APPLICATION: with spatula - trowel.

DILUTION: Ready to use.
MEDIUM OUTPUT: 7-8 mq per coat

DRYING: with air at 20°C and 60% relative humidity.
Application at +5° C minimum

out of touch	in the depth	time to paint over
4-5 hrs	18-24 hrs	24-36 hrs

TABLE DIR.2004/42/CE :
A/l-BA Product= Decorative paint
Limits UE(2010)=200 gr/Lt
C.O.V. gr/Lt=130gr/Lt.
Dilution for application= Ready to use.
C.O.V. (ready to be used) gr/Lt.= Max 130gr/Lt.

PREPARATION OF THE SURFACE: On new, well prepared and levelled off surface, apply a coat of Acrylic primer SPECIAL FIXATIVE.

OLD SURFACE: brush thoroughly the surface removing dust, dirt and flaking parts and apply some stucco to level off if necessary. Then proceed as new surface.

APPLICATION CYCLE: Once the surface is perfectly dry, apply a coat of Stucco Veneziano Fondo covering and smoothing the surface evenly.

NOTE: Available in lithographed buckets 4 L.

Keep it in temperature of +5°/+35°C. Protect from frost.

The information contained in this prospectus is, so far as to our knowledge is correct and accurate and must therefore be considered reliable. In any case, we cannot assume any responsibility, as the conditions of use are outside our strict control.



s.r.l. Via Caduti sul lavoro, 4 46019 Viadana (MN) ITALY - Tel. + 39 0375782083 Fax + 39 0375780055 www.sabercolor.com e-mail : info@sabercolor.com



NAME: STUCCO VENEZIANO OPACO

CODE: 224.1000

CLASSIFICATION: Matt acrylic putty for interiors.

KIND OF USE: The product is suitable for the decoration of historic and modern interiors where a very high level finish with excellent visual impact is desired.

COLOUR: White and neutral
Finish: Matt.

CHEMICAL COMPOSITION: Acrylic copolymer, titanium dioxide, lamellar fillers.

SPECIFIC WEIGHT: 1,450 ± 0,050 kg/L

APPLICATION: with spatula - inox trowel.

DILUTION: Ready to use.
MEDIUM OUTPUT: 6-7 mq with two coats

DRYING: with air at 20°C and 60% relative humidity.
Application at +5° C minimum

out of touch	in the depth	time to paint over
30-60 mins	8 hrs	4-6 hrs

TABLE DIR.2004/42/CE :
A/l-BA Product= Decorative paint
Limits UE(2010)=200 gr/Lt
C.O.V. gr/Lt=60gr/Lt.
Dilution for application= Ready to use.
C.O.V. (ready to be used) gr/Lt.= Max 60gr/Lt.

PREPARATION OF THE SURFACE: For new surface with civil plaster, gypsum or stabilized plasterboard, apply a brush coat of acrylic primer Special Fixative.

OLD SURFACE: brush thoroughly the surface removing dust, dirt and flaking parts and apply some stucco to level off if necessary. Then proceed as new surface.

APPLICATION CYCLE: When the surface is perfectly prepared, apply a coat of Stucco Veneziano Fondo with a stainless-steel trowel,

smoothing the surface carefully and avoiding to leave excess material.

When the surface is dry (8 - 10 hours), apply the first coat of Stucco Veneziano opaco with a stainless-steel trowel, evenly covering the surface. When the surface is dry (4 - 6 hours), apply the second coat with an inox spatula or trowel depending on the type of desired texture.

NOTE: Available in lithographed buckets of 1 - 4 - 14 L.

Keep it in temperature of +5°/+35°C. Protect from frost.

The information contained in this prospectus is, so far as to our knowledge is correct and accurate and must therefore be considered reliable. In any case, we cannot assume any responsibility, as the conditions of use are outside our strict control.



s.r.l. Via Caduti sul lavoro, 4 46019 Viadana (MN) ITALY - Tel. + 39 0375782083 Fax + 39 0375780055 www.sabercolor.com e-mail : info@sabercolor.com