

NAME: TEMPESTA DI NEVE

SERIAL CODE: 319

CLASSIFICATION: Decorative glaze based on pearlescent particles and glitters.

KIND OF USE: The product is indicated as a finish layer for the protection and decoration of inner surfaces. Presents a finish of fine particles with high decorative pearlescent effect and micro crystals of high reflectance.

COLOUR: Pearl, gold, gold and pearl.

CHEMICAL COMPOSITION: Particles dispersed in vinyl versatate.

SPECIFIC WEIGHT: 1.030+/-0.050 Kg/lt

VISCOSITY OF PRODUCT: thick

APPLICATION SYSTEM: brush, special spalter.

DILUTION: Ready to use; if necessary, add 3% water, maximum.

MEDIUM OUTPUT mq/lt for coat: 6 - 7 mq/lt for coat.

DRYING: with air at 20°C. Application at +5° C minimum.

out of touch in the depth time to paint over 2-3 h 4-5 h 6-7 h

TABLE DIR.2004/42/CE :

A/l-BA Product= Decorative paint

Limits UE(2010) = 200 gr/lt

C.O.V. gr/Lt = gr/Lt. 100

Dilution for application= 5% with water

C.O.V. (ready to be used) gr/Lt.= Max 100 gr/Lt.

BRILLIANCE: satin, pearlescent.

PREPARATION OF THE SURFACE: If the surface is perfectly stabilized, apply a coat of acrylic primer SPECIAL FIXATIVE and then a coat with roller of uniform white or desired colored primer DAS.

OLD SURFACE: brush thoroughly the surface removing dust, dirt and flaking parts and apply some stucco to level off if necessary. Then proceed as new surface

APPLICATION CYCLES: When the support is prepared apply a coat of Tempesta di Neve Glow with special spalter with short and crossed brush strokes. Going over the surface with spalter without paint to distribute the product on the support for the desired decorative effect.

Wishing to obtain an effect more homogeneus, in the drying phase (between 20-30 mins) pass over the surface with the spalter.

NOTE: Available in lithographed buckets of 14 L, 4 L, 1L.

STABILITY IN STOCK: 1 year at $+5^{\circ}/+25^{\circ}$ C in the oiginal sealed containers. Protect from freezing weather.

All the informations in this card are exact and accurate, as we know, so they must be considered reliable. In any case they can't mean a guarantee from our, as the conditions of its use out of our control.

s.r.l. Via Caduti sul lavoro, 4 46019 Viadana (MN) ITALY - Tel. + 39 0375782083 Fax + 39 0375780055 www.sabercolor.com e-mail: info@sabercolor.com