

Saber S.r.l.

Via Caduti sul Lavoro, 4 - 46019 Viadana (MN) Italy
 Tel: +39 0375 782083 - Fax: +39 0375 780055
 info@sabercolor.com - bernini@pec.sabercolor.com
 Partita IVA e Codice fiscale 00289400202
 Capitale Sociale € 30.000 - REA: MN 127583

TECHNICAL DATASHEET VENESTUK

Cod. 570.1000 – Rev. 09/2022

CLASSIFICATION	Decorative water-based stucco with marble effect.								
KIND OF USE	The product is indicated as a finishing layer for interior walls with smooth surfaces. VENESTUK has an excellent glossy finish with a spatula effect and if applied to several colors at the same time or overlapped, it is possible to obtain valuable marble effects.								
CHEMICAL COMPOSITION	Selected marble powders and organic binder.								
TECHNICAL DETAILS	Appearance: paste Specific Weight: 1,770 +/- 0,050 kg/L Color: White Viscosity of supply: 50000 +/- 5000 cps Brilliance: film asciutto 80-90 gloss (60°)								
APPLICATION	Hand float or stainless-steel spatula.								
DILUTION	Ready to use product.								
MEDIUM OUTPUT	3,5-4 mq/L finished. 2-2,5 mq/KG finished.								
COV READY TO USE	CLASSIFICATION ACCORDING TO DIR. 2004/42/CE - Dlgs 161/06: Cat. A/I-BA DECORATIVE PAINTS Limits EU 2010 200 gr/lt. COV PRODUCT 40 gr/lt								
DRYING	<u>WITH AIR AT 20°C - 60% humidity</u> <table><tr><td>Out of touch</td><td>in the depth</td><td>time to paint over</td></tr><tr><td>30 mins</td><td>48-72 hrs</td><td>8-10 hrs</td></tr></table>			Out of touch	in the depth	time to paint over	30 mins	48-72 hrs	8-10 hrs
Out of touch	in the depth	time to paint over							
30 mins	48-72 hrs	8-10 hrs							
MIN. TEMPERATURE OF APPLICATION	+ 5° C								
PREPARATION OF SURFACE	For new surface with civil plaster, gypsum or stabilized plasterboard, apply a brush coat of acrylic primer SPECIAL FIXATIVE. For old, weak or crumbling substrates, carefully brush the surface, remove all loose or flaking parts and restore the surface with a suitable filler. Apply then a brush coat of acrylic primer SPECIAL FIXATIVE.								
APPLICATION	Apply two or more coats of VENESTUCK with hand float or stainless-steel spatula until you get the desired effect. When the surface is touch dry but not completely dry, polish with stainless steel spatula, taking care to keep the edge of the spatula clean. Once dry, it can be further polished with a fur backing pad or with 4000 or 6000 abrasive paper or with four zeros iron wool.								
CLEANING EQUIPMENTS AND TOOLS	With water immediately after the use.								
NOTE	Available in packaging of: 1L - 4L - 12L - 20 kg								
STORAGE	The product must be kept in its original intact packaging in an environment which must be protected from freezing and excessive heat and therefore at a temperature not lower than +5 °C and not higher than +35 °C. Liquid or solid residues and empty containers must be disposed of according to local regulations. FEAR THE FROST								

The information, data and suggestions contained in this technical sheet are exact and accurate and must therefore be considered reliable and for informational purposes only and in any case they cannot imply a guarantee on our part, being the conditions of use outside our strict control, therefore they do not release the customer from the burden and responsibility of verifying the suitability of the product for the specific intended use.